



TECHNICAL BULLETIN

TAYCHEM F-EXT-C

Silicone Resin Emulsion

Description:

TayChem F-EXT-C is an emulsion-polymerized silane that can be used as a fluorochemical extender for soil release or can be used "as is" for soil release. This product prevents seam slippage, improves pilling with synthetic fabric or fibers, and has excellent antistat properties.

Applications:

TayChem F-EXT-C is a cationic emulsion of a silicone resin formulated as an antislip agent and also as a finishing agent for polyamide carpets to impart properties of soil repellency and pile integrity. Due to the unique colloidal structure of this emulsion, the resinous silicone will coat the fibers to prevent the adhesion of dirt or to impart anti-slip properties. Being cationic, TayChem F-EXT-C should be compatible in reactant-finishing formulations. Major features are:

1.	Effective at low concentrations.
2.	Will not reduce oil repellency.
3.	Soil release properties.
4.	Will not effect cure of cellulotics.
5.	Maintains pile integrity of polyamide carpet.
6.	Compatible with silicone water repellents.
7.	Compatible with fluorochemicals.

Processing:

Polyamide Fiber Or Yarns For Carpets:

TayChem F-EXT-C should be applied after dyeing and prior to stainguard or fluorochemical treatment. It is applicable to stock-dyed fiber, as well as piece goods.

Typical add-on of TayChem F-EXT-C is two to three percent {2-3%} based on the weight of polyamide or polyester. Best application results should be obtained by spray, foam, or pad.

Normal dry conditions are adequate for fixation.

Antislip Agent:

Normally, two to three percent {2-3%} on-weight-of-goods should control slippage of sheer or tightly-woven fabric. Compatibility with other co-applied finishing agents should be evaluated prior to use.



Typical Properties:

Property	Characteristic
Appearance	Clear To Hazy Liquid
Solids Content (%)	Ca. 11
pH Value	Ca. 9.0
Ionic Character	Cationic
Note: These figures are intended as a guide and should not be used in preparing specifications.	

Storage Stability:

TayChem F-EXT-C has a shelf life of at least six {6} months if stored in its original, sealed container at 25°C or 70°F. If the material is kept beyond the recommended shelf life, it is not necessarily unusable, but quality control should be performed on the properties relevant to the application.

Emulsions showing signs of creaming should be agitated before use to assure uniform consistency.

Safety Instructions:

Comprehensive instructions are given in the corresponding Material Safety Data Sheet. This information is available upon request from TayChem Industries, Ltd.

Because we cannot foresee or control the varied conditions under which this information and materials may be used, we do not guarantee the applicability or accuracy of this information or the suitability of our materials in any specific situation. Samples are provided and users should make their own tests to determine the suitability of our materials for their specific purposes. This material is provided without warranty, either expressed or implied, of fitness for a specific purpose and nothing herein shall be construed as a recommendation for uses which infringe valid patents or as extending license under valid patents.

TayChem Industries, Ltd.
3060 Pharr Court North, N.W.
Suite No. 11
Atlanta, Georgia 30305-2054

Toll-Free Telephone No. (866) 794-0004
Local Telephone No. (404) 264-0004
Facsimile No. (404) 264-1816
E-Mail Address: taychemind@aol.com